

High performance "by deformation" tap (sintered steel) for steels, stainless steels. TiCN-MP coating increases tool life and reduces the coefficient of friction.



- Made in Spain
- Precise and long-lasting thread tapping
- TiCNMP coating

**Machine**



**Application**



**Features**



**Properties and benefits**

- + TiCNMP coating : Hardness 3200HV, coefficient of friction 0,20, resistance to heat (400°C). Low friction coefficient. Excellent chip evacuation. Increased tool life.



Code	EAN	Thread	Ø	Pitch	Norm	Drill	L	I	I4	I5	QTY	PCB
960IT9100300050	8420609526862	M	3	0,5	DIN 371	2,80	56	10	2.5	2,70	1	1
960IT9100400070	8420609526879	M	4	0,7	DIN 371	3,70	63	12	2.5	3,40	1	1
960IT9100500080	8420609526886	M	5	0,8	DIN 371	4,65	70	14	2.5	4,90	1	1
960IT9100600100	8420609526893	M	6	1	DIN 371	5,60	80	16	2.5	4,90	1	1
960IT9100800125	8420609526909	M	8	1,25	DIN 371	7,40	90	18	2.5	6,20	1	1
960IT9101000150	8420609526916	M	10	1,5	DIN 371	9,30	100	20	2.5	8,00	1	1
960IT9101200175	8420609526923	M	12	1,75	DIN 376	11,20	110	22	2.5	7,00	1	1
960IT9101400200	8420609526930	M	14	2	DIN 376	13,00	110	25	2.5	9,00	1	1
960IT9101600200	8420609526947	M	16	2	DIN 376	15,00	110	28	2.5	9,00	1	1
960IT9100800100	8420609596353	MF	8	1	DIN 371	7,50	90	18	2.5	6,20	1	1
960IT9101000100	8420609596360	MF	10	1	DIN 371	9,50	90	18	2.5	8,00	1	1
960IT9101200150	8420609596377	MF	12	1,5	DIN 374	11,30	100	22	2.5	7,00	1	1
960IT9101400150	8420609596384	MF	14	1,5	DIN 374	13,30	100	22	2.5	9,00	1	1